



CSK PHILLIPS SELF DRILL

10-16 X 50

10-16 X 75

Coating - Class3 (1000) Salt Spray

Re-Order code- SDCPH1050R-SDCPH1075R

Withdrawal Strength G550 Steel Framing

Steel Thickness	mean (y) (N)
0.75	1712
0.95	2480

Shear Strength G550 Steel Framing

Steel Thickness	mean (y) (N)
0.75	4460
0.95	5312

Fasteners tested in accordance with

AS1649-2001 AS 1649—2001. Australian Standard™. Timber—Methods of test for mechanical fasteners and connectors
—Basic working loads and characteristic strengths NZS 3603:1993 Timber Structures Standard New Zealand standar