



# HEX SELF DRILL STEEL

## 10-16 X 16

### Coating - Class3 (1000) Salt Spray

Re-Order code- SDHWFS1016R

#### *Withdrawal Strength G550 Steel Framing*

Steel Thickness	mean (y) (N)
0.75	1712
0.95	2480

#### *Shear Strength G550 Steel Framing*

Steel Thickness	mean (y) (N)
0.75	3665
0.95	5369

Fasteners tested in accordance with

AS1649-2001 AS 1649—2001. Australian Standard™. Timber—Methods of test for mechanical fasteners and connectors  
—Basic working loads and characteristic strengths NZS 3603:1993 Timber Structures Standard New Zealand standard