



WAFER PHILLIPS SELF DRILL

10-24 X 30

Coating - Class3 (1000) Salt Spray

Re-Order code- SDWAFS1030F

Withdrawal Strength G550 Steel Framing

Steel Thickness	mean (y) (N)
0.75	1648
0.95	2307

Shear Strength G550 Steel Framing

Steel Thickness	mean (y) (N)
0.75	3607
0.95	4924

Fasteners tested in accordance with

AS1649-2001 AS 1649—2001. Australian Standard™. Timber—Methods of test for mechanical fasteners and connectors
—Basic working loads and characteristic strengths NZS 3603:1993 Timber Structures Standard New Zealand standar