

WAFER PHILLIPS DUAL THREAD BLACK **10-16 X 16**

Coating - Class3 (1000) Salt Spray

Re-Order code- SDWAFS1016DUB

Withdrawal Strength G550 Steel Framing

| Steel Thickness | mean (y) (N) |
|-----------------|--------------|
| 0.75 | 1817 |
| 0.95 | 2270 |

Shear Strength G550 Steel Framing

| Steel Thickness | mean (y) (N) |
|-----------------|--------------|
| 0.75 | 3724 |
| 0.95 | n/a |

Fasteners tested in accordance with

AS1649-2001 AS 1649—2001. Australian Standard™. Timber—Methods of test for mechanical fasteners and connectors —Basic working loads and characteristic strengths NZS 3603:1993 Timber Structures Standard New Zealand standar

Hardie Fasteners Ltd 62 Morrin Road St Johns Auckland

0800 hardie technical@hardiefasteners.co.nz www.hardiefasteners.co.nz